



Date : 23-01-2026

Product	% > 1.7 mm screen	% > 500µm screen	% Fe ₂ O ₃	% CaO	% MgO	% SiO ₂	≥ 85	≥ 15	≤ 0.70	% Moisture
							CaCO ₃	MgCO ₃	% CaCO ₃ +MgCO ₃	
KuluCAG	0	21	0.125	48.94	1.44	3.16	87.39	3.03	90.43	0.31
	Nil	≤ 50.0						≤ 15	≥ 85	≤ 0.70